



CHALKBOARD PAINT K308

Features

- Goes on easily and is washable
- Resists spattering during application
- Zero VOC, Low odour
- Available in any colour
- Dries to a decorative finish that is extremely durable
- Is formulated to minimize lingering odours
- Soap and water clean-up
- Dries quickly

General Descriptions

Chalkboard Paint (308) is acrylic-based topcoat and turns virtually any interior surface into a chalkboard.

Recommended For

For interior use on previously painted surfaces. Use wherever a chalkboard finish is desired.

Limitations

- Do not apply when air and surface temperatures are below 10 °C (50 °F).

Product Information

Colours — Standard: N/A	Technical Data Base 1X
— Tint Bases: 1X, 2X, 3X and 4X	Vehicle Type 100% Acrylic
— Special Colours: None	Pigment Type Titanium Dioxide
Certification VOC compliant in all regulated areas Zero VOC (No VOC added, less than 5g/L per EPA Method 24)	Volume Solids 40%
	Coverage per 3.79 L at Recommended Film Thickness 9.3 - 10.2 sq. m (100 – 110 Sq. Ft.)
Customer Information Centre: 1-800-361-5898, info@benjaminmoore.ca , www.benjaminmoore.ca	Recommended Film Thickness – Wet 3.8 mils – Dry 1.5 mils
	Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.
<div style="border: 1px solid green; padding: 5px; width: fit-content; margin: 0 auto;"> Qualifies for LEED® Credit (INTERIOR NON-FLAT) </div>	Dry Time @ 25° C (77 °F) @ 50% RH – To Touch 2 Hours – To Recoat 4 Hours
	Allow painted area to cure for 3 days before using. Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.
	Dries By Evaporation, Coalescence
	Viscosity 95 ± 2 KU
	Flash Point None
	Gloss / Sheen Eggshell
	Surface Temperature at Application – Min. 10° C (50° F) – Max. 32.2° C (90° F)
	Thin With Clean Water
	Clean Up Thinner Clean Water
	Weight Per 3.79 L 4.8 kg (10.5 lbs)
	Storage Temperature – Min. 4.4° C (40° F) – Max. 32.2° C (90° F)
	<p style="text-align: center;">Volatile Organic Compounds (VOC)</p> <p style="text-align: center;">0g/L</p> <p style="text-align: center;">Zero VOC Post tint (any base and any colour)</p>

◇ Reported values are for Base 1X. Contact Benjamin Moore for values of other bases or colours.

Chalkboard Paint K308

Surface Preparation

Surfaces must be clean, dry and free of wax, grease, dust, mildew, water-soluble materials and scaling paint. Hard, glossy areas should be dulled with sandpaper to ensure proper adhesion.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ http://www.hc-sc.gc.ca/ewh-semt/contaminants/lead-plomb/asked_questions-questions_posees-eng.php

Primer/Finish Systems

Use the appropriate Benjamin Moore® Fresh Start® primer if a primer is required. Follow label directions. For previously painted surfaces in good condition, apply one or two coats of this product. Otherwise, before and after filling in nail holes, cracks and other surface imperfections, spot prime with the appropriate Benjamin Moore® Fresh Start® primer. When dry, apply one or two finish coats of Chalkboard Paint (308).

Application

Stir thoroughly. Apply one or two coats. For best results, use a Benjamin Moore® custom-blended nylon/polyester brush, Benjamin Moore® short nap roller, or a similar product. This product can also be sprayed. When brushing or rolling, apply generously using short overlapping strokes, always moving from unpainted into painted areas. Do not over apply. Let paint dry before touching up. Do not apply in temperatures below 10° C (50° F).

Before Using

Allow painted area to cure for 3 days before using. Prior to initial use, rub entire surface with a piece of white chalk and then erase using a clean, damp cloth. Because of the additives used in some varieties of chalk, which can leave a residue when erased, we recommend using lighter coloured chalk designed for use on chalkboards.

Thinning/Clean Up

Thinning is unnecessary, but if required to obtain desired application properties, a small amount of clean water may be added. Never add other paints or solvents. Wash painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting or follow state/local guidelines on solvent use.

Environmental, Health & Safety Information

Use only in a well ventilated area. Keep container closed when not in use. In case of spillage, absorb with inert material and dispose of in accordance with local regulations. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

SEE MATERIAL SAFETY DATA SHEET