



MARINE FLUORESCENT ENAMEL PAINT 35 – 2100 SERIES

THE PRODUCT: A high quality daylight fluorescent and reflectance alkyd enamel. For use where high visibility is required. Formulated for interior, exterior and marine application.

INTENDED USES: For interior and exterior surfaces on properly primed surfaces. For use on fire-protection, life-saving equipment, navigational aids, ect.

Not recommended for floors, concrete and alkaline surfaces, immersion service or chemical fumes.

Note: IT IS ESSENTIAL THAT A COAT OF WHITE FLAT UNDERCOAT (35-0677) BE APPLIED TO ALL SURFACES BEFORE APPLICATION OF THE FLUORESCENT ENAMEL AS THE UNDERCOAT CONTRIBUTES TO THE REFLECTANCE OF THE SYSTEM

COLOUR:

35-2101 Flame Orange 35-2107 Lightning Yellow
35-2108 Ember Pink 35-2104 Flare Orange
35-2105 Signal Green 35-2110 Horizon Blue

GLOSS: Satin Finish

COVERAGE:

Theoretical: 19.8 m²/L 807 ft² / U.S.Gal)

SOLIDS: 69.3% by weight, 53.7% by volume.

WEIGHT: 1.175 – 1.185 Kg/L

FLASH POINT: 48-53°C (118-127°F)

SURFACE PREPARATION: Surface to be painted must be clean, dry and free of oil, grease and other contamination.

Apply one coat of white undercoat (35-0677) before applying fluorescent enamel..

Repaint Surface Preparation: Wood and metals - Sand glossy areas, remove all chalking and peeling paint. Remove all loose dirt, dust, etc and spot prime all bare areas.

APPLICATION: Formulated for brush, roller or spray application.

THINNING: C.C.C. 85-0303 reducer for brush or roller up to 5%. For spray up to 15% max.

RECOMMENDED FILM THICKNESS: 1.5 to 2.0 mils dft.

NUMBER OF COATS: One coat is usually sufficient.

DRY TIMES: Touch dry 1 – 2 hours.
Hard Dry 14 – 18 hours.
Recoat in 2 - 3 hours.

CLEAN UP: Use C.C.C. 85-0311 reducer.

The technical data furnished above by The Paint Shop is provided for information purposes only and is, to the best of our knowledge, correct. Since application methods and conditions are beyond our control we cannot offer a guarantee or warranty, representation or condition, express or implied, whether arising by statute, by operation of law, or otherwise, (including merchantability or fitness for a particular purpose) with respect to this product and we assume no responsibility or liability of any kind for coverage, performance or damage (whether arising from negligence of the vendor or otherwise) resulting from the installation, operation, use or performance of this product.